

CAS# 111-20-6



## Sebacic Acid Technical Granular

### PRODUCT DATA SHEET

PARAMETERS	SPECIFICATION
Appearance	White Granules
Purity, %	99.5 min
Acid Value	550 min
Ash Content, ppm	250 max
Moisture, %	0.3 max
Color APHA	15 max
Melting Point, °C	131 min

#### **Inquiries:**

Acme-Hardesty Co.  
450 Sentry Parkway  
Blue Bell, PA 19442  
(800) 223-7054  
[csc@acme-hardesty.com](mailto:csc@acme-hardesty.com)

The data herein are based on our current knowledge and believed to be reliable. They are intended for use by persons having technical skill and at their own discretion and risk. Due to numerous factors that may affect handling, processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any data given herein may change without prior notice and do not constitute a contractual agreement regarding quality.

Acme-Hardesty Co., specifically disclaims any implied warranties of merchantability, suitability or fitness for a particular purpose or application, and assumes no liability in connection with the use of this information. Final determination of suitability is the sole responsibility of the user who alone knows the conditions of intended use.

Date: September 26, 2014  
/2053